



WORKWEAR FABRIC INFORMATION

FABRIC	CHARLOTTE
FINISH	Crease Resist
PRODUCT CODE	0163 74



FABRIC CHARACTERISTICS

BLEND	50% Polyester 50% Cotton
FINISHED WEIGHT	180 g/m ²
YARN COUNT	warp Nm 44 weft Nm 44
FINISHED CONSTRUCTION	warp 50 threads/Cm weft 25 threads/Cm
WEAVE	Twill 2X1 Z
MINIMUM USABLE WIDTH	150 cm

PHYSICAL PERFORMANCE	TEST METHOD	PRE-TREATMENT	RESULTS	ETSA RATING
TENSILE STRENGTH	ISO 13934 - 1		warp 750 N weft 450 N	*** N/A*
PILLING MARTINDALE	ISO 12945 - 2 , 5000 Rev	5X ISO 15797	3/4	***
SHRINKAGE IN WASHING	ISO 15797	5X @ 75°C	±2.5	***
WASH & WEAR / CREASE RECOVERY	ISO 15487	3X ISO 15797	3	***


COLOUR PERFORMANCE	TEST METHOD	PRE-TREATMENT	RESULTS	ETSA RATING
RUBBING DRY	ISO 105 X 12		4	N/A*
WASHING	ISO 105 C06 E1S	colour change	4	N/A*
	ISO 105 C06 E1S	colour staining Polyester	3/4	N/A*
	ISO 105 C06 E1S	colour staining Cotton	3/4	N/A*
	ISO 105 D 01	colour change	4	N/A*
DRY CLEANING	ISO 105 E 04	colour change	4	N/A*
	ISO 105 E 04	colour staining Polyester	3/4	N/A*
	ISO 105 E 04	colour staining Cotton	3/4	N/A*
LIGHT FASTNESS	ISO 105 B 02		5	N/A*

NOTES Colour performance results shown are average values. Dark and special colours may not meet figures quoted.

CARE LABELING - Domestic wash



QUALIFICATION SYMBOL - Industrial laundering



NOTES

Characteristic may vary within commercial tolerances.
PRODUCT CARE - ALL FABRICS ARE ALSO TESTED TO KLOPMAN TEST METHODS.



DATE: nov 28 2012



This document is for information only. For a controlled document please contact our technical service.
 N/A* Not available for this product

